

BACKLIT SB MATT 205 micron / 275 g/m²

For use in thermal and piezo inkjet printers.
Solvent, Eco-Solvent, Latex and UV curable inks.

2017 Data-sheet



TEPEDE EDC s.r.o.
Pluhová 2, 831 03 Bratislava, Slovakia
T: +421 233 004 183
F: +421 233 004 184
E: tepede@tepede.com

Material description

The special instant dry translucent polyester coated backlit film, designed for top quality graphic arts applications in light boxes.

The semi-matte coating reduces glare, provides high quality image density, vivid colors, and outstanding image resolution with/ without light.

It is easy to install because of very good rigidity and flatness.

Qualifications

- A fine Semi-Matt Finish Backlit film
- Polyester base material
- Print side : matt white surface
- Reverse side : White gloss
- Perfect density for lightbox applications
- Suitable printing condition : temperature 15-30° / humidity 30-60°
- Over laminating will prolong the durability of the print
- Ambient temperature and weather can affect the condition of the product

Indoor

This material is suitable for indoor displays.

No lamination is required, this means a convenient and low cost method of producing indoor displays.
(It is difficult or impossible to remove dirt or stain from the surface, lamination will protect the material)

Outdoor

This material is suitable for outdoor displays.

For total waterproof protection always use a suitable lamination.

Specifications

Quality		PET
Weight		275 g/m ²
Thickness	ASTM D645	205 um
Print side		Semi Matt instant dry coating
Reverse side		White gloss
L.a.b	ANSI T	85/1/-7 (D50/20/Abs/No)
yellowness	ASTM D1925	30
glossiness	ASTM 2457	5/8

Applications

- Outdoor – indoor light box signage
- Illuminated displays
- Trade show and exhibition graphics
- Signage
- Cosmetics
- Fashion image
- Air port image application
- Bus / metro shelters
- Department store displays

Compatibility

HP, EPSON, CANON, MUTOH, MIMAKI,
ROLAND, SEIKO, OCE
HP LATEX and more

- ☞ Eco Solvent
- ☞ UV curable
- ☞ Solvent
- ☞ Latex

BACKLIT SB MATT 205 micron / 275 g/m²

For use in thermal and piezo inkjet printers.
Solvent, Eco-Solvent, Latex and UV curable inks.

2017 Data-sheet



TEPEDE EDC s.r.o.
Pluhová 2, 831 03 Bratislava, Slovakia
T: +421 233 004 183
F: +421 233 004 184
E: tepede@tepede.com
W: www.tepede.com

Guidelines

Printing

Always choose the right media for the right job.
There are different kinds of inks with different kind of properties.
When printing with UV stable pigment ink it's normal that the colours are different that the dye inks.

Light stability

The light stability of a plot depends on various factors such as dye inks, UV pigmented inks and media coating but the most important factor is direct sunlight. Direct sunlight and UV will cause visible media deterioration on unprotected media within a few weeks or longer.

Mechanical resistance

To protect the print against scratches and damage, it is recommended that media should be handled and used in a clean environment.

Water resistance

Backlit SB matt shows high resistance to fingerprints, smudges and condensation when the plot is completely dry, however direct contact with water for longer period is not recommended.

After printing

To prevent smears, let your prints dry completely.
When laminating (cold) let your prints dry 20 minutes before starting to laminate.

Best view side

The matt (print) side is the best view side . The film is designed for back illumination , the reflected light gives you yield what you expected.

Trouble shooting

Check that the media compatible with your printer and ink.
Choose the right print mode. Check the media setting (if this exists) coated paper, film, etc.
Perform cartridge alignment procedure if necessary.
If required clean the cartridges.

Color calibrations

As with all inkjet media , the product should be calibrated to the printer , to get the best result.

Loading instructions

The rate which ink consumed over a given area varies between different printers and printer set-ups. Backlit SB matt has excellent ink absorption capacity. When loading the media use the right set-up (mode) that gives the highest quality output.

Printer setting and ink quantity

For optimum results, select the highest print quality.
Avoid 3 colour composite black , use single colour black only.

Shelf life and environment aspects

The shelf life of TEPEDE media is 1 year under normal conditions (10-25% at a relative humidity of 30-75%). Higher humidity and/or temperature can affect the product performance.
Always store the media in a dark place.

Ecology

The media and the final plots can be handled and disposed of as photographic colour film or other similar inkjet film media. For the treatment of ink or ink residue, please refer to your printed manual or supplier.

Help available

If there are questions about media, just ask the TEPEDE sales department. They will inform you properly about our media program.

Note

Specifications subject to change without notice.

