

CANVAS ARTIST SB II 338 g/m2 / 393mic

For use in thermal and piezo inkjet printers.
Solvent , Eco-solvent,UV ,Latex based inks.
Latex ink

2017 Data-sheet



TEPEDE EDC s.r.o.
Pluhová 2, 831 03 Bratislava ,Slovakia
T: +421 233 004 183
F: +421 233 004 184
E: tepede@tepede.com

Material description

The Canvas Artist SB II is a lightweight s high-performing , Poly/cotton blend canvas with a 1-over-1 weave and semi-matt finish.(35% cotton ,65% polyester 1:1 structure) with a high –resolution inkjet coating for digital fine art and photographic reproductions.

It is perfect for high-value products created in high production enviroment, and is well-suited for gallery wraps, décor, point-of-purchase, and more.

Besides Solvent, Eco-solvent , UV inks, the product allows very good result with HP latex Ink.

Qualifications

- Blend of polyester and cotton yarns
- Natural structure and matt finish
- Top coated , for vivid colours and sharp egde definitions
- Pre-Stretched quality
- Uniform in texture and perfect stretchable
- Dimensional stable
- Fast drying
- Brilliant colours
- Water-resistant (smudge proof)

Indoor

Lamination is not required and not recommended. If future protection is desired, i tis easily done with lacquer.

For indoor banner applications , the canvas can be sewn and punched.

Outdoor

No suitable for outdoors

Specifications

Base		Polycotton cloth Cotton/Polyester 35% 65%
Weave		1x1
Coating		One Acrylic/ Latex Primer basecoat latex and solvent printable topcoat
Appearance		Natural White / Semmi-matt
Weight		338 g/m2
Thickness		393 mic
Whiteness		85
Brigthness		87
L.a.b		93/-0,5/-0,7
Gloss		60%-4

Applications

- Digital fine arts
- Digital photography
- Reproductions
- Exhibitions
- Indoor banners
- Photographic and artistic prints
- Murals
- Wall covering

Compatibility

HP, EPSON, MUTOH, MIMAKI,
ROLAND,SEIKO,VUTEK,DURST,EFI and more...

- ☞ Solvent
- ☞ Eco-solvent
- ☞ HP Latex
- ☞ UV –curable

CANVAS ARTIST SB II 338 g/m² / 393mic

For use in thermal and piezo inkjet printers.
Solvent , Eco-solvent,UV ,Latex based inks.



TEPEDE EDC s.r.o.
Pluhová 2, 831 03 Bratislava ,Slovakia
T: +421 233 004 183
F: +421 233 004 184
E: tepede@tepede.com
W: www.tepede.com

2017 Data-sheet

Guidelines

Material handling

Canvas has a special inkjet coating that can be damaged by excessive handling. Always handle the media by the edges. Use cotton gloves to prevent fingerprints on the media.

Printing

Always choose the right media for the right job. There are different kinds of inks with different kind of properties. Also look at the compatibility list for this. Leave the textiles in the closed plastic bag for at least 24 hours in the print room. Due to the natural components of the material it tends to curl when relative humidity is quite high, which can cause print head damage. We recommend that the material is first removed from original packaging when printing commences.

Light stability

The light stability of a plot depends on various factors such as dye inks, UV pigmented inks and media coating but the most important factor is direct sunlight. Direct sunlight and UV will cause visible media deterioration on unprotected media within a few weeks or longer. We recommend that images subjected to such conditions. The expected durability of the media is many years.

Water resistance

Canvas shows resistance to fingerprints and smudges when the plot is completely dry, but direct contact with water is not recommended.

After printing

To prevent smears, let your prints dry completely. If you intend to apply a protective spray, allow your prints to dry 20 minutes before doing so.

Handling

Avoid physical damage, such as creasing or folding especially at corners and edges. Any loose threads should be removed before printing to prevent contact with cartridges or other components. Do not remove the paper liner (if this exist) direct after printing. Wait until the textile is completely dry.

Trouble shooting

Check that the media compatible with your printer and ink. Choose the right print mode. Check the media setting (if this exists) coated paper, film, etc. Perform cartridge alignment procedure if necessary. If required clean the cartridges.

Color calibrations

As with all inkjet media, the product should be calibrated to the printer, to get the best result.

Loading instructions

Switching off the cutter is recommended. The rate which ink consumed over a given area varies between different printers and printer set-ups. Material has excellent ink absorption capacity. When loading the media use the right set-up (mode) that gives the highest quality output. Switching off the cutter is recommended.

Printer setting and ink quantity

For optimum results, select the highest print quality. Avoid 3 colour composite black, use single colour black only.

Shelf life and environment aspects

The shelf life of TEPEDE media is 1 year under normal conditions (10-25% at a relative humidity of 30-65%). Higher humidity and/or temperature can affect the product performance. Always store the media in a dark place.

Storage

Store textiles in the right conditions: temperature 20°C/68°C and Relative humidity 35% - 65%. Leave the textiles in the closed plastic bag for at least 24 hours in the print room. Put always textile back in the plastic bag and in the box with the enclosed end – caps. This will protect the textile for future use. **Never leave textiles in the printer after printing!** Textile is more subjected to temperature and humidity changes than other media.

Ecology

The media and the final plots can be handled and disposed of as photographic colour canvas or other similar inkjet canvas media. For the treatment of ink or ink residue, please refer to your printed manual or supplier.

Help available

If there are questions about media, just ask the TEPEDE sales department. They will inform you properly about our media program.

Note

Specifications subject to change without notice.